



STANDARD SURFACE TREATMENT

2-pack system acc. to ISO 12944

Type C3-M

Sandblasting to Sa2½

110µm Epoxy primer

50µm Polyurethan enamel

Type C4-M

Sandblasting to Sa2½

60µm Zinc epoxy primer

90µm Epoxy mid coat

50µm Polyurethan enamel

Type C4-H, C5i-M og C5m-M

Sandblasting to Sa2½

60µm Zinc epoxy primer

130µm Epoxy mid coat

50µm Polyurethan enamel

Type C5i-H og C5m-H

Sandblasting to Sa2½

60µm Zinc epoxy primer

100µm Epoxy mid coat

100µm Epoxy mid coat

60µm Polyurethan enamel

Type C4-L (Heat resistant to 600°C)

Sandblasting to Sa2½-3

60µm Galvosil

Other special surface treatments on inquiry.

Any RAL-colour can be chosen for the top coat, except metallic or fluorescent colours.

Rev. 26-05-201